Nº 032-2000 / Tev.1



Al Composition

Specific gravity g/см3

Tensile strength Rm MPa

Elongation. A50, % min

Material Thickness, mm

Outside diameter, mm

Inside diameter, mm

Weight without liner, g.

Internal lacquer type

External lacquer type

Anisothropy, % max

Al Condition

Height, mm

Shell Material

H14

2.71

≥3

≤2

110-150

0.22 ±0,01 Closure Characteristics

Ø 31.5 ±0.4

44 ±0.2

Ø 31+0.4

3.6 ± 15%

Resins obtained from monomers without any phenols or phthalates.

Mod. polyester

Mod. polyester


EN AW-8011A

Product:

Bottle Neck finish:

DIN 6094-7; GME 305C; GF 305

Pilfer – Proof 31.5 x 44 mm



Ø30.5min internal perforations

Ø31min internal

Recommended application details:	Head pressure force, N Side roller pressure force, N Undertuck roller pressure force, N	1000 - 1200 70 - 100 70 - 100
Removal Torque:	Bridges Breaking Torque, Nm	0.88 - 2.01

NOTE: REMOVAL TORQUES ARE DEPENDANT ON VARIATIONS IN GLASS AND APPLICATION CONDITIONS

LINER			
Liner material:	Foam (Expande) Polyethylene (EPE)		
Liner thickness, mm	1.6± 10%		
Liner weight, g	0.2 ± 1%		
User has to verify the closures suitability with the specific bottled product and to guarantee the absence of chemical and organoleptic alterations.			

Food Contact Approval: All materials intended to come into contact with food are in conformity with the European Community directives, the relevant national regulations and the relevant FDA requirements.

All products comply with Commission directive 94/62/EC concerning heavy metals.

- All resins and additives used for inside lacquer production comply with the following Regulations:
 - Commission directive 2002/72/ EC of 6 August 2002 relating to plastic materials and articles intended to come into contact with foodstuffs.
 - FDA regulation; CFR 21, chapter 175.300 Resinous and polymeric coatings

Packaging specification					
Quantity, pcs.	1400	Pallet type – Euro pallet	Dimension 1200 x 800 x*		
Box Dimension, mm	600 x 400 x 370 mm	* Height of the pallet may vary with customers' requirements			
Cardboard Type Polyethylene Sack	Corrugated five layer cardboard Polyethylene –non-toxic, antistatic <100 ppm Pb, Cd, HgCr ⁺⁶	Outside packing	Stretch wrapped		
Adhesive Strip (Scotch) Product Identification	dhesive Strip (Scotch) 50 mm	Pallet identification	Labeling		

Notes: Closures shall be stored in a well-ventilated place avoiding direct sunlight and strong odour for the period of 1 year. Pallets shall not be stacked.